

TECHNICAL DATA SHEET

HD T9

HD T9 is a stretched tape/raffia grade HDPE manufactured using the Spherilene Technology. This grade is characterized by excellent processability and mechanical strength.

HD T9 can be used for stretched tape/raffia for woven sacks and tarpaulin.

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg, 190° C)	ASTM D 1238	g/10 min	1.1
Density (at 23°C)	ASTM D 1505	g/cm ³	0.950
Physical Property			
Tensile Strength at Yield**		MPa	21
Tensile Strength at Break**	ASTM D 638	MPa	38
Elongation at Break**		%	>1000
Izod Impact Strength (Notched, 23 ° C)	ASTM D 256	J/m	400
Flexural Modulus	ASTM D 790	MPa	1000
Hardness	ASTM D 2240	Shore D	65
DSC Melting Temperature	ASTM D 2117	°C	131
Suggested Processing Conditions			
Barrel Temperature		°C	200 – 240
Die Temperature		°C	230 – 250
Quench Temperature		°C	30

* Halene H is the registered trademark of High Density Polyethylene of HPL

** Tensile Properties are on Compression Molded Type IV Specimens as per ASTM D 638

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.