

TECHNICAL DATA SHEET

71601W

71601W is a LLDPE blown film grade produced by the Spherilene Technology with controlled morphology, excellent processability & mechanical properties

This grade can be used in General Purpose Adhesive Lamination film

71601W is without slip or antiblocking additives

BIS Designation Code: IS 7328-2B-FBE-BDA

Property	Test Method	Unit	Nominal Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238, IS 13360 (Part 4/Sec 1)	g/10 min	1.0
Melt Flow Index (5 kg, 190°C)			2.6
Melt Flow Index (21.6 kg, 190°C)	ASTM D1238	g/10 min	23
Density (23°C)	ASTM D1505, IS 13360 (Part 3/Sec 11)	g/cm ³	0.920
DSC Melting Temperature	ASTM D3418	°C	125
Film Property **			
Tensile Strength at Yield MD	ASTM D882 (500 mm/min)	MPa	10
Tensile Strength at Yield TD		MPa	10
Tensile Strength at Break MD		MPa	25
Tensile Strength at Break TD		MPa	16
Elongation at Break MD		%	650
Elongation at Break TD		%	750
Elmendorf Tear Strength MD	ASTM D1922	g	150
Elmendorf Tear Strength TD		g	400
Dart Impact Strength, F ₅₀ (38 mm Dart, 66 cm Height)	ASTM D1709A	g/μm	4.0
Gloss at 60°	ASTM D2457	GU	76
Suggested Processing Conditions			
Barrel Temperature	180 – 200 °C		
Melt Temperature	190 – 210 °C		
Blow up Ratio	2.0 – 3.0		
Die Gap	2.0 – 2.5 mm		

* Halene L is the registered trademark of Linear Low Density Polyethylene of Haldia Petrochemicals Limited



Halene – L*

** Typical values with 25 µm film made with 2.5 mm die gap & BUR 2.5

This grade meets the requirements of:

IS 7328:2020 Specification for Polyethylene Material for Moulding and Extrusion

IS 16738:2018 Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals

IS 10146 for use in contact with foodstuffs, pharmaceuticals and drinking water

This product is not recommended for manufacturing of Single Use Plastic (SUP) items listed under Plastics Waste Management (PWM) Rule 2016 and its latest amendment

The information and data presented herein are typical values of representative samples and should not be construed as specification or tested values of supplied product. Prior to use, buyer shall ensure independently through tests and trials, that HPL products can be handled and used by them legally, safely, and suitably for their intended operation and end-use application. No warranty or guarantee expressed or implied is made regarding performance or otherwise. In no event shall HPL be liable for any damage, loss or injury directly or indirectly suffered as a result of use of product or information provided herein. The information & data contained herein are reliable to the best of our knowledge on the date of release of the document and is subject to change without prior intimation based on research & development work undertaken by HPL

Compliance Certificates & MSDS are available on request.
Visit us at www.haldiapetrochemicals.com