

TECHNICAL DATA SHEET

M5601

M5601 is a broad molecular weight distribution HDPE Grade produced by Mitsui CX Process

M5601 is suited for both injection & compression molded caps & closure application for Carbonated Soft Drink (CSD), water, juice & beverages

The precise control of morphology & broader MWD during polymerization confers superior processability, good organoleptic, high environmental stress crack resistance & improved performance properties.

This grade does not contain slip agent

BIS Designation Code: IS 7328-3B-CB-FXDA

Property	Test Method	Unit	Nominal Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238, IS 13360 (Part 4/Sec 1)	g/10 min	1.2
Melt Flow Index (5 kg, 190°C)		g/10 min	5.0
Density (23°C, Annealed)	ASTM D1505, IS 13360 (Part 3/Sec 11)	g/cm ³	0.954
Density (23°C, Annealed)	JIS MCI HZ-F-109	g/cm ³	0.958
Physical Property			
Tensile Strength at Yield	ASTM D638 (50 mm/min)	MPa	28
Elongation at Yield		%	9.5
Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	50
Flexural Modulus	ASTM D790A	MPa	1000
ESCR (F ₅₀ , 10% Igepal soln. v/v)	ASTM D1693B	Hr	400
Vicat Softening Point (10 N)	ASTM D1525	°C	124
Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	67
DSC Melting Temperature	ASTM D3418	°C	131
Suggested Processing Conditions			
Barrel Temperature	160 – 190 °C		

*Halene H is the registered trademark of High-Density Polyethylene of Haldia Petrochemicals Limited

Mechanical Properties are on specimens from Compression Molded sheet prepared in accordance with ASTM D4703

This grade meets the requirements of:

IS 7328:2020 Specification for Polyethylene Material for Moulding and Extrusion

IS 16738:2018 Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals

IS 10146 for use in contact with foodstuffs, pharmaceuticals, and drinking water.

This product is not recommended for manufacturing of Single Use Plastic (SUP) items listed under Plastics Waste Management (PWM) Rule 2016 and its latest amendment.

The information and data presented herein are typical values of representative samples and should not be construed as specification or tested values of supplied product. Prior to use, buyer shall ensure independently through tests and trials, that HPL products can be handled and used by them legally, safely, and suitably for their intended operation and end-use application. No warranty or guarantee expressed or implied is made regarding performance or otherwise. In no event shall HPL be liable for any damage, loss or injury directly or indirectly suffered as a result of use of product or information provided herein. The information & data contained herein are reliable to the best of our knowledge on the date of release of the document and is subject to change without prior intimation based on research & development work undertaken by HPL

Compliance Certificates & MSDS are available on request.
Visit us at www.haldiapetrochemicals.com