

TECHNICAL DATA SHEET

M307

M307 is a **Heterophasic Polypropylene Impact Copolymer** produced by the **Spheripol Technology**

M307 combines excellent processability with low Cycle Time

M307 is recommended for General Purpose Injection Molding

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg & 230 ^o C)	ASTM D1238	g/10 min	7
Density at 23°C	ASTM D1505	g/cm ³	0.90
Tensile Strength at Yield	ASTM D638	MPa	23
Tensile Elongation at Yield		%	6
Flexural Modulus	ASTM D790	MPa	950
Izod Impact Strength (Notch, 23°C)	ASTM D256	J/m	80
Vicat Softening Point (10N)	ASTM D1525	°C	145
Heat Deflection Temperature (0.46 N/m ²)	ASTM D648	°C	88

Suggested Processing Temperature

Barrel Temperature	°C	180 – 260
Mold Temperature	°C	30 – 40

* Halene P is the registered trademark of Polypropylene of HPL

Mechanical properties tested on Injection Molded Test Specimens

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.
Visit us at www.haldia Petrochemicals.com