

## TECHNICAL DATA SHEET

## M340

**M340** is a **Heterophasic Polypropylene Impact Copolymer** produced by the **Spheripol Technology**

**M340** combines excellent processability with high Flow, low Cycle Time, excellent Impact – Stiffness balance, Low Warpage and good Gloss

**M340** is recommended for Injection Molded Appliance & White Goods Components, Automotive Components, Thin Walled Injection Molding (TWIM), Compounds

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg & 230 <sup>0</sup> C)	ASTM D1238	g/10 min	40
Density at 23°C	ASTM D1505	g/cm <sup>3</sup>	0.90
Tensile Strength at Yield	ASTM D638	MPa	24
Tensile Elongation at Yield		%	5
Flexural Modulus	ASTM D790	MPa	1200
Izod Impact Strength ( Notch, 23°C)	ASTM D256	J/m	60
Vicat Softening Point (10N)	ASTM D1525	°C	140
Heat Deflection Temperature (0.46 N/m <sup>2</sup> )	ASTM D648	°C	88

### Suggested Processing Temperature

Barrel Temperature	°C	160 – 250
Mold Temperature	°C	30 – 40

\* Halene P is the registered trademark of Polypropylene of HPL

Mechanical properties tested on Injection Molded Test Specimens

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.  
Visit us at [www.haldia Petrochemicals.com](http://www.haldia Petrochemicals.com)