

TECHNICAL DATA SHEET

M5002L

<p>M5002L is a Narrow MWD HDPE produced by Spherilene Technology</p> <p>M5002L is suited for injection and extrusion-compression molded Caps & Closures</p> <p>The precise control of morphology & MWD during polymerization confers superior processability, excellent organoleptics & improved performance properties compared to conventional HDPE grades</p> <p>BIS Designation Code: IS 7328-3B-CB-EDB</p>			
Property	Test Method	Unit	Nominal Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238, IS 13360 (Part 4/Sec 1)	g/10 min	3
Melt Flow Index (5 kg, 190°C)			8
Melt Flow Index (21.6 kg, 190°C)	ASTM D1238	g/10 min	70
Density (23°C)	ASTM D1505, IS 13360 (Part 3/Sec 11)	g/cm ³	0.950
Physical Property			
Tensile Strength at Yield	ASTM D638 (50 mm/min)	MPa	25
Tensile Strength at Break		MPa	30
Elongation at Break		%	700
Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	180
Flexural Modulus	ASTM D790A	MPa	950
Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	74
Vicat Softening Point (10 N)	ASTM D1525	°C	125
DSC Melting Temperature	ASTM D3418	°C	132
Hardness	ASTM D2240	Shore D	61
Suggested Processing Conditions			
Barrel Temperature	160 – 190 °C		

* Halene H is the registered trademark of High Density Polyethylene of Haldia Petrochemicals Limited

Mechanical Properties are on Injection Molded test specimens prepared as per ASTM D4101

This grade meets the requirements of:

IS 7328:2020 Specification for Polyethylene Material for Moulding and Extrusion



Halene – H*

IS 16738:2018 Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals

IS 10146 for use in contact with foodstuffs, pharmaceuticals and drinking water

This product is not recommended for manufacturing of Single Use Plastic (SUP) items listed under Plastics Waste Management (PWM) Rule 2016 and its latest amendment

The information and data presented herein are typical values of representative samples and should not be construed as specification or tested values of supplied product. Prior to use, buyer shall ensure independently through tests and trials, that HPL products can be handled and used by them legally, safely, and suitably for their intended operation and end-use application. No warranty or guarantee expressed or implied is made regarding performance or otherwise. In no event shall HPL be liable for any damage, loss or injury directly or indirectly suffered as a result of use of product or information provided herein. The information & data contained herein are reliable to the best of our knowledge on the date of release of the document and is subject to change without prior intimation based on research & development work undertaken by HPL

Compliance Certificates & MSDS are available on request.
Visit us at www.haldia Petrochemicals.com